

## OlyBond 500™ SpotShot

### GENERAL:

OlyBond 500 SpotShot is a two-component, polyurethane construction grade, low-rise expanding adhesive designed for bonding insulation to various substrates. OlyBond 500 SpotShot is compatible with: Wood Fiberboard, polyisocyanurate insulation, EPS, extruded polystyrene, DensDeck® Strataguard™ and OSB. Compatible deck types include concrete, cellular lightweight concrete, gypsum, cementitious wood fiber, wood and painted or galvanized steel. OlyBond 500 SpotShot is also compatible with the following roofing materials: smooth BUR (previously exposed), mineral cap sheet, smooth (previously exposed) or granulated Mod-Bit and Air and Vapor Barrier. OlyBond 500 SpotShot is applied in beads or ribbons 6" or 12" o.c. depending on the wind zone, building height and code requirements to produce a strong adhesive bond between the insulation and the substrate. Factory Mutual approval over a variety of deck types and substrates has been achieved.

### TYPICAL PROPERTIES AND CHARACTERISTICS\*\*:

Base	Part A (1) Polymeric Isocyanate	Part B (2) Polyols, Surfactants & Catalysts
Mixing Ratios by Volume	1:1 Part A to Part B	
Viscosity (CPS@25°C)	225	275
Avg. Net Weight	10.32 lbs/gal	8.54 lbs/gal
Packaging	0.2 gal per cartridge (0.75 L)	0.2 gal per cartridge (0.75 L)
Shelf Life	1 year	1 year

### CAUTIONS AND WARNINGS:

- Review the applicable Material Safety Data Sheet for complete safety information prior to use.**
- The foam produced is an organic material. It must be considered as combustible and may constitute a fire hazard. The foam adhesive must not be left exposed or unprotected. Shield from heat and sparks.
- Do not smoke during application.
- Use with adequate ventilation. Avoid breathing vapors. Wear a NIOSH or MSHA approved respirator for organic vapors with prefilters and solvent resistant cartridges. Proper safety training is essential for all persons involved in the installation process. If inhaled, remove to fresh air and administer oxygen if breathing is difficult. Consult a physician immediately.
- Avoid contact with eyes. Safety glasses or goggles are required. If splashed in eyes, immediately flush eyes with plenty of clean water for at least 15 minutes. Contact a physician immediately.
- Avoid contact with skin. Wear long sleeves and pants. Wash thoroughly after handling. In case of contact with skin, thoroughly wash affected area with soap and water or corn oil. NOTE: Versico's special solvent resistant Hycron® or nitrile gloves are required when handling Part A directly.
- Job site storage temperatures in excess of 90 °F (32 °C) may affect product shelf life. Should the components be stored at temperatures lower than 55 °F (13 °C), restore to room temperature prior to use. Do not allow OlyBond 500 SpotShot to freeze.
- All air intake vents on roofs must be closed during application of OlyBond 500 SpotShot.
- KEEP OUT OF THE REACH OF CHILDREN.**

**COVERAGE RATE:** For standard 12" o.c. bead application (may vary due to job site conditions)

Insulation attachment to:

Gypsum, lightweight concrete, concrete, wood, steel,  
smooth (previously exposed) BUR, Mod-Bit, mineral cap, or  
multiple layers of insulation.

Per carton - 4 cartridge sets  
400 to 600 sq.ft.

## APPLICATION:

1. The surface to which the adhesive is to be applied shall be smooth, dry, free of fins, sharp edges, loose and foreign materials, oil and grease and standing water. All sharp projections and loose material shall be removed by sweeping, blowing or vacuum cleaning.
2. Adhesion tests must be conducted on lightweight concrete and gypsum decks to determine deck integrity prior to using the OlyBond 500 SpotShot product for insulation securement.
3. Proper adhesion of existing roof coatings to their substrate must be verified prior to bonding to these materials.
4. Fibrous cement decks must be investigated for their ability to retain liquid adhesive. (Some types of fibrous cement decks may allow liquid adhesive to flow through the deck).
5. Apply a 1/2" to 3/4" wide bead of OlyBond 500 SpotShot (standard or winter version) when the substrate and ambient temperature is 0° F (-18° C) or above.
6. Select the appropriate version of OlyBond 500 SpotShot based on the forecasted temperatures.
  - OlyBond 500 SpotShot (40° F and above / 4° C)
  - OlyBond 500 SpotShot Winter (0° to 40° F / -18° to 4° C)

## Insulation Attachment

1. Apply OlyBond 500 SpotShot using a portable 1:1 applicator (oversized, dual-cartridge caulking gun)\* with beads spaced as outlined on the following chart:

<b>Building Height</b>	<b>Bead Spacing (Perimeter)</b>	<b>Bead Spacing (Field)</b>
0 – 25 feet	6 inches o.c. - 4 feet perimeter	12 inches o.c.
25 – 50 feet	6 inches o.c. - 8 feet perimeter	12 inches o.c.
50 – 75 feet	6 inches o.c. - 12 feet perimeter	12 inches o.c.
75 – 100 feet	6 inches o.c. - 16 feet perimeter	12 inches o.c.
100 feet or greater	Contact Versico for bead spacing requirements	

When following Factory Mutual guidelines, bead spacing in the perimeter and corner areas may differ from the table above.

2. Place 4' x 4' maximum insulation boards into OlyBond 500 SpotShot after allowing it to rise between 1/2" to 3/4" and develop string/body (approx. 1.5 - 2 min. at room temperature) but before the adhesive reaches a "tack-free" state.
3. Designate one person to walk and roll boards into place using a 150 lb. weighted roller adding constant weight or slitting boards where necessary until adhesive sets-up.

\* The portable 1:1 applicator (available through OMG Incorporated) is a hand operated, lightweight, portable unit that consists of an oversized, dual-cartridge caulking gun used to transfer the 2-component OlyBond 500 SpotShot adhesive from the plastic cartridges to the substrate. From the applicator, the adhesive flows through a disposable static mixing nozzle and onto the substrate. Since the adhesive reaction occurs in the nozzle, clean up and maintenance is fast and easy. Each carton includes 4 tube sets and 6 static mixing tubes.

\*\* General properties. Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification or specification range for any particular property of this product.

Hycron is a trademark of Becton Dickinson & Company.  
StrataGuard is a trademark of Owens Corning Corporation.  
DensDeck is a trademark of G-P Gypsum Corporation.  
OlyBond 500 is a trademark of Olympic Manufacturing Group.  
© 2007 Versico Incorporated