

VERSICO'S ONE-PART POURABLE SEALER



Overview

Let Versico simplify your next VersiGard EPDM installation with their One-Part Pourable Sealer. One-Part Pourable Sealer is a single component, moisture curing, elastomeric polyether sealant that is compatible with Versico's EPDM membranes. The material is designed to provide a flexible, durable and long lasting seal around hard-to-flash penetrations in VersiGard Roofing Systems. One-Part Pourable Sealer provides rapid skin time when exposed to atmospheric moisture forming a waterproof rubber surface in less than one (1) hour. Moisture curing continues, until a two (2) - inch deep solid rubber seal encases the penetration. Complete cure time will vary depending on relative humidity and temperature.

The sealant's one-part, pourable consistency allows for quick pocket filling without mixing. Versico's V-150 Primer must be applied to all EPDM surfaces, including cured membrane and uncured flashing, that will be in contact with One-Part Pourable Sealer. V-150 Primer should not be applied to the plastic (HDPE) strip that is part of the Versico Pourable Sealer Pocket. Unused sealant remaining in a pouch will remain useable up to 30 days if pouch is resealed with original cap.

Intended Uses

Versico's One-Part Pourable Sealer is designed to provide a flexible, durable and long lasting seal around hard-to-flash penetrations in VersiGard Roofing Systems.

Features and Benefits

- Ready to use - no mixing required
- Pouch can be resealed with original cap
- Provides a flexible, durable and long lasting seal around hard-to-flash penetrations
- Provides a water-tight seal in less than one hour

Application *

1. Bonding surfaces must be free of moisture, dirt, or any contaminants. Any previously applied asphalt, caulking, or sealants must be removed from the penetration(s).
2. Fill any voids in the roof deck around the penetration(s) to prevent sealant from seeping through roof. Install appropriate QA Pourable Sealer Pocket or metal dam in accordance with the appropriate C-16 detail. Minimum pourable sealer depth is 2" (50 mm). Minimum distance from object to side of pocket is 1" (25 mm).
3. Versico's V-150 Primer must be applied to all EPDM surfaces, including cured deck membrane and uncured flashing, that will be in contact with One-Part Pourable Sealer. V-150 Primer should not be applied to the plastic (HDPE) strip that forms the inside wall of the QA pourable sealer pocket. Allow primer to dry.
4. Remove cap from 0.5-gallon (2-liter) pouch and pour One-Part Pourable Sealer directly into pocket. Fill pocket completely until rim is covered with One-Part Pourable Sealer making sure all voids are filled.
5. To save unused sealant, squeeze air from pouch and replace cap. Unused sealant should be used within 30 days.

* REVIEW CURRENT VERSICO SPECIFICATIONS AND DETAILS FOR SPECIFIC APPLICATION REQUIREMENTS



A SINGLE SOURCE FOR SINGLE-PLY ROOFING

Versico, LLC PO Box 1289, Carlisle, PA 17013
Tel: **800.992.7663** Fax: 717.960.4036 Web: **www.versico.com**

Precautions

1. Review the applicable Material Safety Data Sheet for complete safety information prior to use.
2. Avoid breathing vapors. Keep container closed when not in use. Use with adequate ventilation. If inhaled, remove to fresh air. If not breathing, perform artificial respiration. If breathing is difficult, give oxygen. Call a physician immediately.
3. If swallowed, DO NOT INDUCE VOMITING. Call a physician immediately.
4. Avoid contact with eyes. Safety glasses or goggles are recommended. If splashed in eyes, immediately flush eyes with plenty of clean water for at least 15 minutes. Contact a physician immediately.
5. Avoid contact with skin. Wash hands thoroughly after handling. In case of contact with skin, thoroughly wash affected area with soap and water.
6. Do not thin. Thinning will affect performance.
7. Shelf life is based on storage in original, unopened or undamaged containers at temperatures ranging from 60°F to 80°F (15°C to 26°C). Should the One-Part Pourable Sealer be exposed to lower temperatures, restore to room temperature prior to use.
8. Coverage rates are average and may vary due to conditions of the job site.
9. Avoid contact of Pourable Sealer to surfaces other than rubber surfaces. Staining will occur.
10. KEEP OUT OF THE REACH OF CHILDREN.

Coverage Rates

One 0.5-gallon pouch (2-liter) will fill 122 cubic inches of volume within a pourable sealer pocket. For example, one (1) 6" pourable Sealer Pocket (56 cubic inches) will require 0.23 gallons (0.87 liters) of pourable sealer to fill completely (with no penetrations).

TYPICAL PROPERTIES AND CHARACTERISTICS

Specific Gravity	1.4 (11.6 lbs/gallon) - 1.5 (12.5 lbs/gallon)
Viscosity (Brookfield RTV), cps	Self leveling 20,000 - 50,000
Color	Black
Odor	Mild ester smell (mint) when wet. Odorless when dry
Elongation @ Break, % ASTM D-0412	450 - (7 day ambient cure)
Hardness, (Shore A) ASTM C-0661	25 - 35
Tack Free Time ASTM C-0679	Less than 1 hour - @ 70 degrees F.
Low temperature flex PASS	Minus 20 degrees F.
Shrinkage (14 day cure)	No measurable shrinkage
Service temperature ASTM 2453	Minus 40 degrees F to 200 degrees F.
Long term weatherability ASTM G53	No crazing or cracking - 98 cycles @ 12 hours/cycle - (condensate exposure - 4 hrs @ 50°C) - (U.V. exposure - 8 hrs @ 70°C)
Packaging	4-0.5 gallon pouches per bucket
Weight Per Carton	29 lbs. / bucket
Shelf Life (unopened container)	12 months