

# VERSICO'S V-150 PRIMER



## Overview

Let Versico simplify your next VersiGard® EPDM installation with our V-150 Primer. Versico's V-150 Primer is a solvent-based product designed for one-step cleaning and priming of EPDM surfaces prior to the application of Quick-Applied (QA) Seam Tape and all other QA or peel-and-stick (P&S) products. V-150 can also be used with Versico's Splice Adhesive.

## Intended Uses

Versico V-150 Primer is designed for one-step cleaning and priming of EPDM surfaces prior to the application of Quick-Applied (QA) Seam Tape and all other QA or peel-and-stick products.

## Features and Benefits

- One-step cleaner and primer used in conjunction with all quick-applied or peel-and-stick accessories on EPDM membranes
- Coverage rates of up to 450 square feet per gallon with no-dust membrane

## Application \*

1. Remove all foreign material by wiping with a clean rag.

If membrane is very dirty, scrubbing with Weathered Membrane Cleaner may be necessary. This process is essential on membrane that has been exposed for a number of weeks.

Note: Permeation-resistant gloves (that meet ANSI/ISEA 105-2005) are recommended when cleaners or primers are being used.

2. Thoroughly stir primer until all settled materials are blended into the solution.

3. Application of V-150 Primer:

A. Standard VersiGard Membrane - Apply the primer with a clean Splice Wipe (or equivalent). Scrub the area of the membrane (where the QA Seam Tape or quick-applied, peel-and-stick product or Splice Adhesive is to be applied) in a circular motion to achieve a thin, even coating on the membrane. The properly cleaned/primed area will be uniform in color without streaks and free of globs or puddles.

B. No-Dust Membrane - Roller-apply the primer to the membrane with a short nap-length paint roller. The coated area will be free of globs or puddles.

NOTE: The use of excessive amounts of V-150 Primer will not significantly enhance the adhesion of the QA Seam Tape, quick-applied or peel-and-stick products to the EPDM membrane. Use only the amount necessary to obtain 100% coverage of the area where the tape or adhesive will be applied.

4. Allow the V-150 Primer to dry until it does not transfer to a dry finger touch. Installation of the QA Seam Tape, quick-applied or peel-and-stick product as soon as the primer flashes off minimizes potential dust contamination and promotes adhesion in colder weather.

5. Complete the splice as specified in Versico's Specifications and Details.
- \* REVIEW CURRENT VERSICO SPECIFICATIONS AND DETAILS FOR SPECIFIC APPLICATION REQUIREMENTS.

## Precautions

1. This product is FLAMMABLE. Precautions must be taken to keep the primer away from heat, flame and sparks during storage and use.
2. Keep container closed when not in use. Use with adequate ventilation. Avoid breathing vapors. Avoid contact with eyes and skin.
3. If inhaled, remove to fresh air. If not breathing, perform artificial respiration. If breathing is difficult, give oxygen. Call a physician immediately. During application, efforts must be made to prevent fumes from entering the building via air ventilation ducts. Do not place open containers or mix adhesive near fresh-air intake units. When possible, shut down or seal off the closest units.
4. If swallowed, DO NOT INDUCE VOMITING. Call a physician immediately.
5. Chemical-resistant gloves must be worn with V-150 Primer to protect hands from staining and irritating ingredients.
6. Thoroughly stir this product until all settled pigment is blended into the solution. Solids suspended in V-150 Primer tend to settle; stir the solution frequently during use (every 15-20 minutes). Use V-150 full strength. Do not thin. Thinning will affect performance.
7. Versico V-150 Primer may cause staining of VersiGard White membrane and other non-black surfaces.
8. Jobsite storage temperatures in excess of 90°F (32°C) may affect product shelf life. Should the primer be stored at temperatures lower than 60°F (15°C), restore to room temperature prior to use.
9. Keep can tightly closed when not in use and protect from moisture contamination. Once exposed to moisture in the air, V-150 begins to cure and may gel within a few days. A gasket of membrane or sealant can be used to create a positive seal.

10. Due to solvent flash-off, condensation may form on freshly applied V-150 Primer when the ambient temperature is near the dew point. If condensation develops, the application of primer must be discontinued (proper adhesion will not be obtained). Allow the surface to dry and apply a thin freshener coat of primer to the previously coated surface when conditions allow.

11. REVIEW THE V-150 PRIMER MATERIAL SAFETY DATA SHEET FOR COMPLETE SAFETY INFORMATION PRIOR TO USE.

12. KEEP OUT OF THE REACH OF CHILDREN.

## Mixing

Stir thoroughly until all settled pigments are dispersed and the primer is uniform in color. Minimum five (5) minutes of stirring is recommended.

## Coverage Rates

Approximately 250 sq ft/gallon (23 sq m) can be expected when properly applied to dusted membrane. Coverage rates as high as 450 sq ft/gallon (42 sq m) can be expected with No-Dust membrane.

V-150 PRIMER TYPICAL PROPERTIES AND CHARACTERISTICS**	
Base	Synthetic Rubber
Color	Olive drab to dark gray
Solids	18%
Flash Point	40°F (4.4°C)
VOC	727 grams/liter
Packaging	1-gallon (3.8-liter) cans or 2½-gallon (9.5-liter) pails
Shelf Life	9 months
Average Weight	7.3 lbs/gallon (0.9 kg/liter)

\*\* Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification or specification range for any particular property of this product.